

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H05K 3/02, 3/46, B32B 31/00	A1	(11) International Publication Number: WO 99/53737
		(43) International Publication Date: 21 October 1999 (21.10.99)

(21) International Application Number: **PCT/US99/07795**
(22) International Filing Date: 9 April 1999 (09.04.99)

(30) Priority Data:
09/058,262 (10 April 1998 (10.04.98) US
09/182,956 (29 October 1998 (29.10.98) US
09/193,461 (17 November 1998 (17.11.98) US
09/210,349 (11 December 1998 (11.12.98) US

(71) Applicant: R.E. SERVICE COMPANY, INC. [US/US]; 400 South Beckman Road, Lodi, CA 95240 (US).

(72) Inventor: FRATER, Mark, S.; 9556 Springfield Way, Stockton, CA 95212 (US).

(74) Agent: O'BANION, John, P.; Gerber, Ritchey & O'Banion LLP, Suite 1550, 400 Capitol Mall, Sacramento, CA 95814 (US).

(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published


With international search report.

Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(54) Title: **STEEL ALLOY SEPARATOR SHEETS AND COPPER/STEEL LAMINATED SHEETS FOR USE IN MANUFACTURING PRINTED CIRCUIT BOARDS**

(57) Abstract

A corrosion resistant steel alloy separator sheet (12) for use in a press lay-up between printed circuit board panels, a sheet laminate (10) for use in a press lay-up between printed circuit board panels having a steel alloy layer (12) and a copper foil layer (14) releasably bonded to at least one surface of the substrate layer, and a sheet laminate (10) for use in a press lay-up between printed circuit board panels having a metal substrate (12) layer releasably bonded to the copper foil layer (14) by a plurality of metal-to-metal bonds (16) disposed along the boundary (18) of the copper foil layer (14) such that gaps (20) are defined between the bonds (16).



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

STEEL ALLOY SEPARATOR SHEETS AND
COPPER/STEEL LAMINATED SHEETS FOR USE IN
MANUFACTURING PRINTED CIRCUIT BOARDS

5 BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention pertains generally to circuit board fabrication, and more particularly to a steel alloy separator sheets and copper/metal laminated structures for use in the manufacture of printed circuit boards.

10 2. Description of the Background Art

In early stages of manufacturing technology, printed circuit board (PCB) lay-up panels were laminated using presses similar to those used in the wood industry for laminating, for example, sheets of plywood. Hydraulic-driven presses were used, and steam or electric power was used to heat the presses to
15 temperatures exceeding 350° F. The panel components in the presses were submitted to pressures between 300 psi and 500 psi at 350° F for approximately one hour to achieve lamination. Highly polished and precision ground stainless steel plates approximately 0.062 inches thick were used to separate each panel within a press opening. Typically, a T-304 full hard alloy or equivalent material
20 was used for these 0.062 inch stainless steel separator plates. A problem, however, was that these stainless steel 0.062 inch separator plates required cleaning or scrubbing to remove debris after every use and periodically needed to be resurfaced to remove dents and scratches due to handling and use. Eventually, the plates had to be replaced.

25 During the late 1980's, the introduction of vacuum assisted presses permitted the use of lower pressures during the lamination cycle. The pressures used in vacuum assisted presses typically ranged from approximately 150 psi to 250 psi, as opposed to the 300 psi to 500 psi range used in the hydraulic steam driven or electric presses. With vacuum assisted presses, aluminum separator
30 sheets ranging in thickness from 0.007 to 0.015 inches were tested and then used extensively. Test results published during that time indicated that thin aluminum separator plates far exceeded the performance of steel plates for laminating PCB panels. These thin aluminum separator sheets were discarded after the

lamination process, thus eliminating the need for expensive steel plate cleaning and handling operations and the frequent and high capital investment needed to replace the steel plates. The alloy used for aluminum separator plates is typically 3000 series (e.g. 3003, 3004, 3105 or equivalent) with a H19 hardness designation, which is identical to the alloy used to make aluminum beverage cans. The process using thin aluminum separator sheets along with low pressure from vacuum assisted presses has worked well for typical 4 layer to 6 layer PCB's with circuit lines of approximately 0.008 inches in width and approximately 0.008 inches apart. A typical configuration in a press opening would be a steel plate on top and bottom of the stack with thin aluminum sheets separating each PCB panel. The rate of production in these vacuum assisted presses increased to about 10 - 14 PCB panels per typical 1-1/2 inch press opening from the 6 to 8 PCB panels achieved using 0.062 inch stainless steel sheets.

Technological advancements, however, have driven a need for PCBs having more and denser circuitry. This means that circuits must have finer lines (less than 0.006 inches wide) and closer spacing between circuit lines (less than 0.006 inches). Denser surfaces on a PCB permit a higher quantity of electrical components to be mounted thereon, thus enabling faster information processing and greater miniaturization of electronic hardware. These greater technological demands have made the surface quality of the laminated circuit board panels even more critical. Problems such as surface roughness and image transfer that also previously existed, have now become critical issues that require resolution, as any minute bump on the surface of the aluminum sheet will be transferred to the top surface of the board necessitating scraping the board and reworking the PCB fabrication process.

To prevent and minimize scrap and rework due to image transfer and surface quality problems, almost every press configuration used today employs 0.062 inch stainless steel plates (usually T-304 or T-600 stainless steel) placed adjacent to the thin aluminum separator sheets in addition to on the top and bottom of the stack. Many press loads have at least three steel plates added to the lay-up, which then reduces the number of panels that can be laminated in each press cycle. Some of the lay-up configurations have both aluminum sheets and steel plates separating every panel in the press, with the aluminum separator

sheets being discarded after the press cycle. This approach, however, has not completely cured the problem as it causes a decrease in the production rate of the press. Also, pits, dents and other surface imperfections due to the re-introduction of steel plates into the process are still causing scrap and rework of PCB panels.

5 Moreover, many PCB fabricators have to purchase additional new 0.062 inch stainless steel plates and again install expensive plate cleaning and handling systems. Although the thin aluminum separator sheets are discarded after every press cycle, the steel plates must be cleaned before each use, adding additional operational steps and cost to the PCB fabrication process. To maintain production
10 demands, fabricators must purchase additional vacuum presses, at a cost of approximately \$250,000 to \$1,000,000 per unit, to compensate for the loss of productivity due to the re-introduction of steel plates into the PCB fabrication process.

Today, fabricators are producing between 3 and 8 PCB panels on high
15 technology dense boards with more quality problems and at a high cost. Dense state of the art PCB's now require 2 separators, an 0.062 inch stainless steel plate and a thin sheet of aluminum. This is an expensive step backward to the beginning of the evolution of the PCB fabrication process.

Use of a thin piece of aluminum in a copper/aluminum laminate structure
20 simply does not meet today's demanding requirements for high technology, dense PCB's. Such laminates suffer from a number of drawbacks which include susceptibility to print through and image transfer, misregistration, blistering, warpage and delamination. In addition, they exhibit unacceptable surface roughness.

25 Off contact printing often results from image transfer. This generally inhibits the adhesion of dry film and the ability to expose a one to one image on panels. As a result, such laminates are typically limited to fabricating four to six layer PCB's. In addition, shims are often required between every PCB panel. The use of shims adds significant cost to PCB manufacture. The shims must go through a
30 labor intensive cleaning process between each use. Shims are very expensive and many PCB manufacturers have had to set aside space in their manufacturing facilities for shim cleaning.

Misregistration results from too much movement in the inner layers. This causes drill breakage and renders the PCB useless. Drill breakage also results from misregistration in high technology PCBs where small holes which are less 13 mils and as small as 4 mils are typical.

5 Bestirring results from the uneven coefficient of thermal expansion exhibited by aluminum. The uneven CTE creates more hot spots which cause blistering. This problem may not even show up for six months or more after fabrication and, therefore, may cause major system failures.

10 Surface roughness is also a problem with aluminum. The high surface roughness will cause off contact printing, broken drill bits, and loss of materials. The laminates are also susceptible to warpage which renders them useless. And, delamination has been observed using the laminates at low pressures.

BRIEF SUMMARY OF THE INVENTION

15 The deficiencies inherent in conventional PCB laminates and lamination processes are overcome by the laminate structure of the present invention which generally comprises a steel alloy separator sheet for attachment to a sheet of copper, as well as a sheet of corrosion resistant metal, other than aluminum or copper, that is attached to a sheet of copper. By way of example, and not of limitation, in accordance with one aspect of the invention the deficiencies are
20 overcome with a sheet of steel alloy material having a corrosion resistant coating and unique metallurgical properties. The steel alloy sheet can be used as a separate component, can be bundled with unattached copper foil, or can be optionally attached to a copper foil layer in any conventional manner using, for example, adhesive materials in the manner described in used in U.S. Patent No.
25 5,153,050, U.S. Patent No. 5,120,590, or U.S. Patent No. 5,512,381. In accordance with another aspect of the invention, the deficiencies are overcome with a laminated construct preferably comprising a steel layer having a corrosive resistant coating, and a copper foil layer attached to the steel alloy layer using similar attachment techniques. Therefore, it does not matter whether the adhesive
30 is applied in a band as described in U.S. Patent No. 5,153,050 to provide a continuous seal, or applied in intermittent spots or islands as described in U.S. Patent No. 5,120,590 where neither a continuous nor substantially continuous seal is provided. Nor does it matter whether the adhesive is flexible or rigid. It will be

appreciated, however, that the adhesive should be of a type that either releases the sheets at press temperatures or otherwise does not interfere with the subsequent separation of the sheets. In accordance with a still further aspect of the invention, the sheets are directly bonded to each other using resistance
5 welding or the like, so that bonding takes place without the use of an adhesive.

In the laminated constructs of the present invention, the copper foil layer is attached to either one or both sides of the steel layer. When heated and compressed onto the PCB panel, the copper adheres to and becomes a functional element of the final PCB. The steel layer is subsequently removed and discarded.
10 Use of the steel layer of the present invention eliminates and/or reduces the need for conventional 0.062 inch stainless steel plates in the press lay-up. As a result, the surface quality of the PCB is improved, image transfer is reduced and a flatter, less wavy PCB is produced without the cost of using separate 0.062 inch stainless steel separator plates. Furthermore, the similarity in the coefficients of thermal
15 expansion (CTE) between steel in accordance with the present invention and copper allows the PCB's produced to be flatter, thus providing for a better registration of the foil layer to the substrate layer of the sheet laminate.

Additional information regarding sheet laminate fabrication technology and processes for manufacturing PCB's can be found in U.S. Patent Nos. 4,875,283,
20 5,120,590, 5,512,381 and 5,153,050.

The steel alloy separator sheet, as well as the copper/steel laminate structures of the present invention exhibit superior performance over copper/aluminum, copper/copper, and other known copper/metal laminate structures. For example, with the laminate structure of the present invention it is
25 possible to manufacture PCBs having up to eighteen layers without the need to use shims. Because the steel sheet used in the present invention does not exhibit the image transfer problems associated with aluminum/copper and copper/copper laminates, the invention also allows more PCBs per book as compared to conventional laminates thereby facilitating increased production. In addition, the
30 steel layer allows PCBs to be run at higher pressures, thereby providing a flatter and more usable PCB area. Furthermore, the need for conventional 0.062 inch stainless steel separator plates is eliminated, with a resulting reducing in material and facility cost. Also, the steel layer used in the present invention exhibits a

more stable heat rise than aluminum, thereby reducing the possibility of misregistration and drill breakage. Blistering and warpage are also reduced because the CTE of the metal substrate of the present invention is similar to that of copper. And, the smooth surface of the steel of the present invention promotes the fabrication of high density PCBs. Also, delamination problems associated with aluminum/copper and copper/copper laminate structures are eliminated.

An object of the invention is to provide a separator sheet for use in a press lay-up between PCB layers, that eliminates the need to use both an 0.062 inch stainless steel and an aluminum separator sheet in PCB fabrication.

Another object of the invention is to provide a sheet laminate, for use in a press lay-up between PCB layers, that eliminates the need for aluminum separator sheets and their associated problems.

Another object of the invention is to eliminate the need for using adhesives between the functional layer and the separator layer of PCB laminate structures.

Another object of the invention is to reduce the amount of waste in PCB manufacturing.

Another object of the invention is to eliminate the surface quality and image transfer problems associated with aluminum separator sheets.

Another object of the invention is to eliminate the need for constant scrubbing and cleaning of conventional 0.062 inch stainless steel separator plates.

Another object of the invention is to provide a sheet laminate, for use in a press lay-up between PCB layers, that eliminates the need for using an adhesive between the functional element and the separator sheet.

Another object of the invention is to provide a sheet laminate, for use in a press lay-up between PCB layers, that eliminates the need for conventional 0.062 inch stainless steel plates and their associated problems.

Another object of the invention is to provide a sheet laminate, for use in a press lay-up between PCB layers, that reduces and/or eliminates image transfer from the substrate layer onto the foil layer.

Another object of the invention is to provide a sheet laminate, for use in a press lay-up between PCB layers, that results in flatter, less wavy PCB panels.

Another object of the invention is to provide a sheet laminate for use in a press lay-up between PCB layers that has a CTE less than or equal to the CTE of

copper.

Still another object of the invention is to provide a sheet laminate, for use in a press lay-up between PCB layers, that maximizes the number of PCB panels that can be produced for a given press opening.

5 Further objects and advantages of the invention will be brought out in the following portions of the specification, wherein the detailed description is for the purpose of fully disclosing preferred embodiments of the invention without placing limitations thereon.

BRIEF DESCRIPTION OF THE DRAWING

10 The invention will be more fully understood by reference to the following drawings which are for illustrative purposes only:

FIG. 1 is a schematic plan view of a directed bonded laminate sheet in accordance with the present invention.

15 FIG. 2 is a cross-section of the laminate sheet shown in FIG. 1 taken through line 2-2.

FIG. 3 is a schematic plan view of an adhesive bonded embodiment of a laminate sheet in accordance with the present invention where the adhesive is applied in discontinuous occurrences.

20 FIG. 4 is a schematic plan view of an adhesive bonded embodiment of a laminate sheet in accordance with the present invention where the adhesive is applied as a band.

DETAILED DESCRIPTION OF THE INVENTION

Referring to FIG. 1 through FIG. 4, where like reference numbers denote like parts, as well as the following technical description, embodiments of the invention comprise a steel alloy separator sheet having a corrosion resistant coating and unique metallurgical properties, as well as a laminate sheet structure comprising a thin sheet of steel material bonded to a thin sheet of copper. It will be appreciated that the apparatus may vary as to configuration and as to details of the parts without departing from the basic concepts as disclosed herein.

30 In FIG. 1 and FIG. 2, a sheet laminate 10 for PCB manufacturing in accordance with the preferred embodiment of the present invention is generally shown. Sheet laminate 10 comprises a metal substrate layer 12 bonded to a copper foil layer 14. In accordance with the invention, metal substrate layer 12

preferably comprises a steel alloy having the properties described herein. And, while the invention is described herein in terms of a copper/metal laminate, it will be appreciated that the inventive concepts apply equally to laminates having additional layers, such as copper/metal substrate/copper laminates typically used
5 in the PCB manufacturing industry.

Copper foil layer 14 can be present on either or both sides of steel layer 12. Use of a steel layer in accordance with the present invention has been found to be superior to the commonly used 0.010 inch to 0.015 inch 3004 aluminum substrate for reducing image transfer and improving surface quality of the PCB,
10 while also significantly improving productivity of PCB panels. Sheet laminate 10 of the present invention is designed for use in both traditional low pressure vacuum presses that operate in the range between approximately 150 psi and 250 psi, as well as high pressure presses up to 500 psi, which is well beyond the capability of aluminum.

15 Nickel or zinc-nickel plated 1008 low carbon steel has been determined to be ideal for meeting the objectives of the invention, although 1001 low carbon steel should also be suitable. The thickness of steel layer 12 can range from approximately 0.002 inches and 0.025 inches, although the preferable thickness range is between approximately 0.005 inches and 0.015 inches. Copper foil layer
20 14 preferably has a thickness ranging from approximately 0.00025 inches to approximately 0.005 inches.

Greater productivity is accomplished, while still meeting the other objectives of the invention, through use of a steel layer 12 that is approximately 0.008 inches thick and this thickness represents the preferred embodiment of the invention.
25 The use of a steel layer approximately 0.008 inches thick eliminates the need or reduces the number of steel plates required in a press lay-up, resulting in a greater number of PCB panels capable of being placed into the press for a given lamination process. The "kiss cycle" during the lamination process, which is a prerequisite for the successful use of aluminum substrates, can also be eliminated as
30 a result of the use of a steel layer in accordance with the invention, thereby reducing the overall production time. The function of the "kiss cycle" is to soften or melt the epoxy before full pressure is applied. Fully liquefied epoxy flows away from the high pressure area into regions between circuits to minimize print

through.

For illustrative purposes, the metallurgical and other characteristics of the preferred steel alloy used in the present invention are compared with aluminum in Table 1.

5 It will be appreciated that the surface of the PCB laminate that is produced is only as smooth as the material that is pressed against it. The surface quality of the PCB laminated with metal substrates is improved significantly by employing a steel layer having a surface finish of no greater than approximately 12 RMS. In comparison, aluminum has a surface finish around 18 RMS to 25 RMS. The issue
10 of surface finish is critical especially when miniaturization is an objective, because the fewer imperfections that exist on the surface of the PCB when dense electrical paths are etched thereon, the more reliable the final PCB product. The steel substrate 12 employed in the present invention also has a low propensity to scratch, pit or dent because it is many times harder than other metals, such as
15 aluminum. Therefore, a PCB laminated with a steel substrate according to the invention will have less likelihood of surface imperfections.

Another the advantage provided by the steel substrate used in sheet laminate 10 is the additional hardness steel offers, along with greater rigidity, which significantly reduces image transfer onto foil layer 14 and ultimately, onto
20 the finished PCB. For purposes of the present invention, a Knoop hardness of approximately 200 for the steel of the invention provides satisfactory results at the desired. A PCB laminated with such a steel substrate is also less wavy as compared to a PCB laminated with an aluminum substrate. It will be appreciated that harder steel substrate is also satisfactory and contemplated within the scope
25 of the present invention. For example, at the specified thicknesses, it is possible to obtain steel substrates from suppliers with Knoop hardness ratings as high as approximately 850. Typically, though, the harder steels this thin are not easily available in the industry. It will further be appreciated that softer steel substrate is acceptable provided that it is not too soft. For example, a steel alloy substrate
30 having a Knoop hardness of approximately 150 should also provide satisfactory results. It will also be appreciated, that the steel substrate of the present invention should be harder than either aluminum or copper to achieve the desired results described herein.

Preferably the steel substrate is plated with nickel or nickel-zinc to provide corrosion resistance, although other common resistant coats, including polymers or electrolyzed aluminum (chrome), could be used. Lead, however, would not be an appropriate material since it is very soft and will bond to the copper foil layer during when heated. An additional surprising characteristic results from nickel plating steel substrate 12; namely, the hardness increases as it gets hotter. For example, the hardness of the nickel plated steel increases by approximately 20% as the substrate is heated to the curing temperature of 350° F. The optimum thickness of the nickel plating is typically between approximately 20μ inches and approximately 50μ inches.

The greater rigidity provided by the steel layer 12 used in the present invention also provides better support for copper foil layer 14 and practically eliminates the bellows-effect associated with aluminum substrates. Because of low rigidity, an aluminum substrate flexes easily and, when flexed, the aluminum substrate momentarily separates from the copper foil layer thereby creating a suction that draws dust and debris into the resultant gaps; that is, a bellows effect occurs. As a result of dust and debris entering the gaps, dent and epoxy spots appear on the finished PCB surface. A complete seal between the steel layer 12 and foil layer 14, which is essential for aluminum substrates, is therefore unnecessary for steel substrates.

Significantly, the atomic crystal lattice patterns for aluminum and nickel plated steel are very different. The atoms in aluminum are arranged in a face centered cubic (FCC) pattern. The atoms in steel, however, are arranged in a body centered cubic (BCC) pattern. The nickel plating on the steel substrate is amorphous with no definite microstructure. This material is not a wrought product and is created by an electrical plating process. These crystal lattice patterns significantly influence the physical and mechanical properties of each material and explain why they present different characteristics in the same heated environment.

The heat transfer characteristics of steel provide a consistent and uniform heat rise with little variability. It is this uniformity in heat rise that reduces PCB panel thickness variations and provides a more consistent lamination quality with the present invention. The steel should have a CTE less than that of copper (e.g. less than approximately 9.8 μinches/°F) so as to allow the copper foil layer to

proportionally register with the steel substrate layer. During the thermal expansion process, copper foil layer 14 moves more than substrate 12, so a substrate material having a CTE equal to or less than copper would optimize registration between the two substances. Substrate 12 preferably has a coefficient of thermal expansion ranging between approximately 6.5 μ inches/ $^{\circ}$ F and approximately 7.5 μ inches/ $^{\circ}$ F. Copper expands to approximately 50% as compared to expansion of aluminum while steel expands to approximately 90% as compared to aluminum. In direct comparison, the CTE of aluminum is 84% greater than that of steel. This means that a 24-inch wide unrestrained sheet of aluminum heated from room temperature (70 $^{\circ}$ F) to curing temperature will have its width increased by approximately 0.090 inches. A steel sheet of identical proportion will have a width increase of approximately 0.049 inches and copper will have a width increase of approximately 0.066 inches. It can be clearly seen that not only are the dimensional differences between copper and steel less than the dimensional difference between aluminum and copper, the steel expands overall less than the copper which has been determined to be preferable. As a result, the PCB's produced using steel substrates are flatter and more uniform as compared with those produced using aluminum substrates.

The primary material for PCB panels is woven fiberglass which is pre-pregated (pre-preg) with a viscous thermosetting resin. Copper from the foil layer in the sheet laminate is transferred onto each face of the pre-preg in the press during lamination. During lamination, the woven fiberglass and resin pre-preg are heated and become a viscous liquid, free to expand along with the metals in the stack. Therefore, no significant stresses are induced into these composite materials by thermal expansion during heat up for curing. Since copper foil layer 14 is very thin compared to steel layer 12, frictional forces will restrain copper foil layer's 14 movement during heating. The copper will therefore yield as the substrate material expands. If the substrate material is aluminum, the copper foil layer will be stretched 0.024 inches over the width of a twenty-four inch circuit board heated to the curing temperature, and uneven localized loading will cause the foil layer to be stretched non-uniformly, more in some areas than others, resulting in a "rippling" or "wavy" effect in the copper foil layer. On the other hand, if the substrate material is steel according to the invention herein, copper foil layer

14 will not be stretched during heating to the curing temperature, and thus no uneven loading will occur on copper foil layer 14 and also blister causing strains in copper foil layer 14 is reduced.

Instead of using an adhesive as is used in conventional laminate structures
5 in the PCB manufacturing industry, steel layer 12 of the present invention is preferably attached to copper layer 14 through the use of a plurality of spaced-apart welds 16. Welds 16 are contact bonds between the surfaces of the materials and generally comprise circular-shaped welds of approximately 4-mils to 20-mils in diameter. In this manner, the surfaces of the two materials are directly
10 bonded without the use of adhesives or other intermediate bonding agents such as solder. While resistance welding is a technique known in other industries, its application to the PCB manufacturing industry is unique.

Resistance welding is a thermoelectric process in which heat is generated by passing an electrical current through the parts to be joined. The process uses
15 electrodes to push the parts together with sufficient force to remove the surface oxides that would otherwise inhibit current flow. Once physical contact is established, a controlled combination of resistance generated heat and physical pressure is applied through the electrodes to create the actual joint. The amount of heat generated is a function of the current applied, the length of time it is
20 applied, and the resistance profile between the parts being joined.

Resistance welding is generally understood as a method for bonding materials in one of three ways. One way is through brazed or soldered bonds, where resistance heating of the parts to be joined generates sufficient heat to melt a third metal, such as silver solder alloy or tin/lead solder that is used as an
25 intermediate bonding agent. A second way is use forge welds where a very short weld-time current is used to forge the parts together without melting them; that is, to establish a metal to metal bond. Forge welds are particularly well suited for joining dissimilar materials. The third way is through fusion bonding where a longer pulse is used to melt both parts to a liquid at their interface point, and the
30 parts are held together as they cool to establish metal to metal bonds. Fusion bonding is particularly well suited for joining two similar materials.

In the preferred embodiment of the invention, the materials are joined using forge welds rather than using fusion bonding or an intermediate bonding agent

such as solder between the materials. It is important that welds 16 be sufficiently weak that, when the laminate structure is placed into the press and the copper is heated and compressed onto the PCB panel, the strong bond between the copper and pre-preg in the PCB panel automatically breaks the welds so that the metal substrate 12 can easily be removed and discarded. For a copper/steel/copper laminate structure using the materials described herein, satisfactory bonds can be achieved using approximately 10.6 watt-seconds of energy and a welding head force of approximately five pounds. These levels are affected by the following variables: the welding energy used to generate heat, the amount of time the energy is applied, the physical weld force that is applied, and the properties of the materials being joined such as metallurgic properties, resistance, thickness, configuration and coatings. Preferably from approximately 5.0 watt-seconds to approximately 25 watt-seconds of energy and approximately two pounds to ten pounds of force should be available to accommodate production variances. Exact values can be determined empirically.

A system suitable for carrying out resistance welding in accordance with the present invention is available from UNITEK, and includes a model 125DP dual pulse power supply with a maximum output of 125 watt-seconds, a model PM7S programmable AC power supply rated at 2 KVA, a model 80A/24 air actuated weld held, rated 125 ws/2kva and 8 ounce to 20 pounds of force, model ESO413 tungsten electrodes, and models EW4002 and HW1090 wheel electrodes. It will also be appreciated that other types of welding techniques could be used, and that the bonds need only be sufficiently strong to remain intact during material handling but be capable of being broken in the press.

Welds 16 are placed around the perimeter of the sheets and within a marginal area 18. While the width of marginal area 18 can be larger if specified by the customer, the present invention permits the use of a smaller marginal area than that commonly found in the industry. More particularly, because of the precision with which the resistance welds can be made, it is possible with the present invention to reduce the width of marginal area 18 to approximately 0.25 inches or less from the outside edge of the sheets if desired. For example, conventional laminate structures typically have marginal areas of between approximately 0.50 inches and 1.0 inches wide, which provides a total overlap of

approximately 1.0 inch s to 2.0 inches. This is due to the flow characteristics of the adhesive leaving a unusable area around the perimeter of the laminate structure. In practice, the unusable marginal area is trimmed away in the manufacturing process, leaving a finished board size. For example, in order to
5 achieve a standard sized 18-inch x 24-inch circuit board panel where adhesives are used, a 19-inch x 25-inch laminate is generally required because there is a 0.50 inch border along each side which is cut away after lamination. Hence, the resistance welding technique of the present invention is advantageous in that it eliminates waste, thus providing a larger effective usable area of the PCB panel.

10 Welds 16 are arranged generally linearly in a plurality of occurrences such that gaps or openings 20 are defined between welds 16. The length of gaps 20 can vary, but would typically range from approximately ½ inch to 2.5 inches depending upon the product type and specification. Apertures 22 along each edge of laminate 10 represent typical tooling positions. Apertures 22 are typically
15 disposed between the outer edges of apparatus 10 and the finished circuit area 24. The finished panel edge 26 is formed after flash trimming by the customer.

Note also that, because use of a steel layer in accordance with the present invention eliminates the bellows effect found in copper/aluminum laminate structures, there is no need for a continuous seal between the layers to guard
20 against entry of dust and debris. Therefore, in the present invention not only is the need for an adhesive eliminated, but the bonding points do not have to form a band around the perimeter of the sheets. And, while welds 16 are shown positioned along all four sides of the structure, they could be alternatively positioned along one side, two opposing sides, two adjacent sides, or along three
25 sides.

Referring now to FIG. 3, for illustrative purposes an alternative embodiment of the invention using an adhesive as a bonding agent is shown. Here, the laminate structure is the same as described previously, except that discontinuous occurrences 28 of adhesive 30 are used instead of welds 16. The adhesive
30 material 30 preferably comprises a rubber compound, as rubber compound adhesives offer more durability in handling prior to its use. Adhesive material 30 is placed around the perimeter of the sheets and within margin 18 that is typically between approximately 0.50 inches and 1 inch wide, depending on end product

and customer requirements. Adhesive material 30 is arranged generally linearly in a plurality of occurrences 28 such that gaps or openings 20 are defined between occurrences 28 of adhesive material 30. The width of adhesive material 30 in each occurrence 28 typically varies between approximately 0.002 inches and approximately 0.100 inches, but is typically between approximately 0.060 inches and approximately 0.090 inches, and the height or thickness is typically between approximately 0.001 inches and approximately 0.003 inches. Each occurrence 28 of adhesive material 30 can take the form of lines, strips or dots. While there is no need to do so using steel layer 12 of the present invention because the bellows effect has been eliminated, adhesive material 30 could alternatively be applied as a continuous band 32 as shown in FIG. 4, as is done with copper/aluminum laminate structures. However, the preferred placement of adhesive 30 would be in a gapped configuration as shown where the occurrences 28 of adhesive material 16 make up between approximately 40% to 60% of the perimeter length, thus leaving gaps 20 formed along 40% to 60% of the perimeter.

Accordingly, it will be seen that this invention provides for joining a steel substrate layer and a copper foil layer using resistance welds for use as a laminate structure that is placed in a press lay-up for lamination to produce PCB panels. In addition, the invention also provides a metal substrate layer that is superior in its characteristics than conventional metal substrate layers. Although the description above contains many specificities, these should not be construed as limiting the scope of the invention but as merely providing illustrations of some of the presently preferred embodiments of this invention. Thus the scope of this invention should be determined by the appended claims and their legal equivalents.

Table 1

	<u>1008 CS STEEL</u>	<u>3004 H-19 ALUMINUM</u>
Composition	Iron and carbon	Aluminum with traces of magnesium and manganese.
Hardness (Knoop)	199-220	60-70
Density (lb/in^3)	0.290	0.098
CTE ($\text{inches}/\text{in}^\circ\text{F}$)	7.2	13.9
Yield Strength (lb/in^2)	133,000	41,000
Tensile Strength (lb/in^2)	140,000	43,000
Modulus of Elasticity (lb/in^2)	29,000,000	10,200,000
Roughness (RMS)	< 12	18-25

CLAIMS

What is claimed is:

1. A separator sheet for use in manufacturing printed circuit boards,
5 comprising a metal substrate, said metal substrate having a Knoop hardness between approximately 150 and approximately 850, said metal substrate having a surface finish of less than approximately 12 RMS.
2. A separator sheet as recited in claim 1, wherein said substrate has a
10 thickness between approximately 0.002 and approximately 0.025 inches.
3. A separator sheet as recited in claim 1, wherein said substrate has a coefficient of thermal expansion less than approximately 9.8 μ inches per °F.
- 15 4. A separator sheet for use in manufacturing printed circuit boards, comprising a metal substrate having a coefficient of thermal expansion less than approximately 9.8 μ inches per °F and a surface finish of less than approximately 12 RMS.
- 20 5. A separator sheet laminate as recited in claim 4, wherein said substrate has a thickness between approximately 0.002 and approximately 0.025 inches.
6. A separator sheet as recited in claim 4, wherein said substrate layer
25 has a Knoop hardness between approximately 150 and approximately 850.
7. A separator sheet for use in manufacturing printed circuit boards, comprising a metal substrate having a coefficient of thermal expansion less than approximately 9.8 μ inches per °F, a Knoop hardness between approximately 150
30 and approximately 850, and a surface finish of less than approximately 12 RMS.
8. A separator sheet as recited in claim 7, wherein said substrate has a thickness between approximately 0.002 and approximately 0.025 inches.

9. A separator sheet for use in manufacturing printed circuit boards, comprising a metal substrate having a coefficient of thermal expansion less than approximately 9.8 μ inches per $^{\circ}$ F, a Knoop hardness between approximately 150 and approximately 850, a surface finish of less than approximately 12 RMS, and a
5 thickness between approximately 0.002 and approximately 0.025 inches.

10. A sheet laminate for use in manufacturing printed circuit boards, comprising:
(a) a metal substrate layer, said metal substrate layer having a
10 coefficient of thermal expansion less than approximately 9.8 μ inches per $^{\circ}$ F and wherein said metal substrate layer has a Knoop hardness between approximately 150 and approximately 850; and
(b) at least one copper foil layer bonded to a surface of said metal substrate layer.

15

11. A sheet laminate as recited in claim 10, wherein said substrate layer has a thickness between approximately 0.002 and approximately 0.025 inches.

12. A sheet laminate as recited in claim 10, wherein said substrate layer
20 has a surface finish of less than approximately 12 RMS.

13. A sheet laminate as recited in claim 10, wherein said copper foil layer has a thickness between approximately 0.00025 and approximately 0.005 inches.

25

14. A sheet laminate for use in manufacturing printed circuit boards, comprising:
(a) a metal substrate layer, said substrate layer having a coefficient of thermal expansion less than approximately 9.8 μ inches per $^{\circ}$ F and a surface finish
30 of less than approximately 12 RMS; and
(b) at least one foil layer of copper bonded to a surface of said metal substrate layer.

15. A sheet laminate as recited in claim 14, wherein said substrate layer has a thickness between approximately 0.002 and approximately 0.025 inches.

16. A sheet laminate as recited in claim 14, wherein said copper foil layer has a thickness between approximately 0.00025 and approximately 0.005 inches.

17. A sheet laminate as recited in claim 14, wherein said substrate layer has a Knoop hardness between approximately 150 and approximately 850.

10

18. A sheet laminate for use in manufacturing printed circuit boards, comprising:

(a) a metal substrate layer which has a coefficient of thermal expansion less than approximately 9.8 μ inches per °F, a Knoop hardness between approximately 150 and approximately 850, and a surface finish of less than approximately 12 RMS; and

15

(b) at least one copper foil layer bonded to a surface of said metal substrate layer.

19. A sheet laminate as recited in claim 18, wherein said substrate layer has a thickness between approximately 0.002 and approximately 0.025 inches.

20

20. A sheet laminate as recited in claim 18, wherein said copper foil layer has a thickness between approximately 0.00025 and approximately 0.005 inches.

25

21. A sheet laminate for use in manufacturing printed circuit boards, comprising:

(a) a metal substrate layer which has a coefficient of thermal expansion less than approximately 9.8 μ inches per °F, a Knoop hardness between approximately 150 and approximately 850, a surface finish of less than approximately 12 RMS, and a thickness between approximately 0.002 and approximately 0.025 inches; and

30

(b) at least one copper foil layer having a thickness between approximately 0.00025 and approximately 0.005 inches bonded to a surface of said metal substrate layer.

- 5 22. A sheet laminate for use in manufacturing printed circuit boards, comprising:
- (a) a metal substrate layer;
 - (b) at least one foil layer of copper disposed over a surface of said substrate layer; and
 - 10 (c) a plurality of spaced-apart welds joining said substrate layer and said foil layer arranged generally linearly along the periphery of said foil layer.

23. A sheet laminate as recited in claim 21, wherein said metal substrate
15 layer has a coefficient of thermal expansion less than approximately 9.8 μ inches per °F and wherein said metal substrate layer has a Knoop hardness between approximately 150 and approximately 850.

24. A sheet laminate as recited in claim 21, wherein said substrate layer
20 has a thickness between approximately 0.002 and approximately 0.025 inches.

25. A sheet laminate as recited in claim 21, wherein said substrate layer has a surface finish of less than approximately 12 RMS.

25 26. A sheet laminate as recited in claim 21, wherein said foil layer has a thickness between approximately 0.00025 and approximately 0.005 inches.

27. A sheet laminate for use in manufacturing printed circuit boards, comprising:
- 30 (a) a metal substrate layer;
 - (b) at least one foil layer of copper disposed over a surface of said substrate layer; and
 - (c) a plurality of metal-to-metal bonds joining said substrate layer and

said foil layer, said bonds arranged generally linearly along the periphery of said foil layer such that gaps are defined between said bonds.

5 28. A sheet laminate as recited in claim 27, wherein said substrate layer has a coefficient of thermal expansion less than approximately 9.8 μ inches per °F and wherein said metal substrate layer has a surface finish of less than approximately 12 RMS.

10 29. A sheet laminate as recited in claim 27, wherein said substrate layer has a thickness between approximately 0.002 and approximately 0.025 inches.

 30. A sheet laminate as recited in claim 27, wherein said foil layer has a thickness between approximately 0.00025 and approximately 0.005 inches.

15

 31. A sheet laminate as recited in claim 27, wherein said substrate layer has a Knoop hardness between approximately 150 and approximately 850.

 32. A sheet laminate for use in manufacturing printed circuit boards,
20 comprising:

- 25 (a) a metal substrate layer which has a coefficient of thermal expansion less than approximately 9.8 μ inches per °F, said substrate layer having a Knoop hardness between approximately 150 and approximately 850, said substrate layer having a surface finish of less than approximately 12 RMS;
- (b) at least one copper foil layer, said foil layer disposed over a surface of said substrate layer; and
- 30 (c) a plurality of metal-to-metal bonds joining said substrate layer and said foil layer, said bonds arranged generally linearly along the periphery of said foil layer such that gaps are defined between said bonds.

33. A sheet laminate as recited in claim 32, wherein said substrate layer has a thickness between approximately 0.002 and approximately 0.025 inches.

34. A sheet laminate as recited in claim 32, wherein said foil layer has a
5 thickness between approximately 0.00025 and approximately 0.005 inches.




FIG. - 1




FIG. - 2




FIG. - 3




FIG. - 4

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/07795

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 H05K3/02 H05K3/46 B32B31/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 H05K B32B B30B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 297 19 716 U (CARL AUG. PICARD GMBH & CO) 11 December 1997 see claims 1,11,14,15 ---	1,3,4,6, 7,9
A	DE 41 16 543 A (SIEMENS NIXDORF INFORMATIONSSYSTEME AG) 26 November 1992 see the whole document ---	1,3
A	PH. E. HINTON: "The high-yield challenge in laminating MLBs" ELECTRONIC PACKAGING AND PRODUCTION., vol. 30, no. 1, January 1990, pages 56-61, XP000096286 MASSACHUSETTS US see page 61, middle column ---	1
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

6 July 1999

Date of mailing of the international search report

06/10/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mes, L

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/07795

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 411 142 A (FANUC) 6 February 1991 see column 4, line 27 - line 54 ----	10,11, 13,22, 24,26, 27,29,30
A	US 5 153 050 A (JOHNSTON) 6 October 1992 cited in the application see claims -----	10,11, 13,22, 24,26
A	GB 1 217 104 A (SIEMENS AG) 31 December 1970 see the whole document -----	22,27
P,X	EP 0 872 301 A (MITSUI MINING & SMELTING CO.) 21 October 1998 see claims -----	10,11, 13,22, 24,26

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PLT/US 99/07795

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 29719716 U	11-12-1997	NONE	
DE 4116543 A	26-11-1992	NONE	
EP 411142 A	06-02-1991	JP 2222597 A JP 2556897 B DE 69012019 D WO 9010369 A US 5482586 A	05-09-1990 27-11-1996 06-10-1994 07-09-1990 09-01-1996
US 5153050 A	06-10-1992	AT 147927 T AU 662012 B AU 2365592 A BG 61363 B BG 98543 A BR 9206474 A CA 2116662 A,C CN 1070076 A,B CZ 283348 B CZ 9400435 A DE 69216839 D DE 69216839 T DK 600925 T EP 0600925 A ES 2096766 T FI 940913 A GR 3022737 T HK 37097 A HU 69843 A JP 6510399 T NO 940657 A SK 22394 A WO 9304571 A US 5725937 A US 5674596 A	15-02-1997 17-08-1995 16-03-1993 30-06-1997 28-02-1995 10-10-1994 04-03-1993 17-03-1993 18-03-1998 15-06-1994 27-02-1997 07-05-1997 07-07-1997 15-06-1994 16-03-1997 25-02-1994 30-06-1997 04-04-1997 28-09-1995 17-11-1994 25-04-1994 10-08-1994 04-03-1993 10-03-1998 07-10-1997
GB 1217104 A	31-12-1970	AT 298594 B BE 730215 A CH 481500 A DE 1765048 A ES 365222 A FR 2004739 A NL 6902665 A SE 365909 B	15-04-1972 01-09-1969 15-11-1969 01-07-1971 16-02-1971 28-11-1969 30-09-1969 01-04-1974
EP 872301 A	21-10-1998	JP 10291080 A	04-11-1998